


In the Claims

1-62 (Canceled).

63. (Currently Amended) A polyurethane-urea elastomeric composition comprising a soft segment and a hard segment, wherein the soft segment is formed from a macrodiamine compound of formula (I):



DI
and a ~~compound selected from the group consisting of a macrodiol, a macrodiamine, and mixtures thereof;~~

wherein

R is hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

~~R₁, R₂, R₃, and R₄~~ ~~R₄, R₃, and R₆~~ are each independently hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₅ and R₆ are each independently an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₇ is a divalent linking group or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical; ~~and~~

n is an integer of 1 or greater; and

wherein the macrodiol is a polysiloxane macrodiol, a polyether macrodiol, a polycarbonate macrodiol, or a mixture thereof;

and wherein the hard segment is formed from:

(i) a diisocyanate; and

(ii) a chain extender comprising the diamine compound of formula (I).

64. (Currently Amended) The composition of claim 63 wherein the diamine compound of formula (I) where n is 1 to 4; and a the molecular weight of the compound of formula (I) is about 500 or less.

65. (Original) The composition of claim 64 wherein R_7 is oxy.

66. (Original) The composition of claim 64 wherein the compound of formula (I) has a molecular weight range of about 60 to about 500.

67. (Original) The composition of claim 66 wherein the compound of formula (I) has a molecular weight range of about 60 to about 450.

DI 68. (Original) The composition of claim 64 wherein the compound of formula (I) is 1,3-bis(3-aminopropyl)tetramethyldisiloxane; or 1,3-bis(4-aminobutyl)tetramethyldisiloxane.

69. (Previously Amended) The composition of claim 64 wherein the chain extender further comprises a second chain extender.

70. (Currently Amended) The composition of claim 69 wherein the second chain extender is a diol, a second diamine, a water chain extender, or a combination thereof.

71. (Original) The composition of claim 70 wherein the diol chain extender is 1,4-butanediol; 1,6-hexanediol; 1,8-octanediol; 1,9-nonanediol; 1,10-decanediol; 1,12-dodecanediol; 1,4-cyclohexanedimethanol; p-xyleneglycol; 1,4 bis (2-hydroxyethoxy) benzene; water; or a combination thereof.

72. (Currently Amdended) The composition of claim 70 wherein the second diamine chain extender is 1,2-ethylenediamine; 1,3-propanediamine; 1,3-butanediamine; 1,6-hexanediamine; 1,2-diaminocyclohexane; 1,3-diaminocyclohexane; or a combination thereof.

73. (Currently Amended) The composition of claim 69 wherein the molar percentage of the chain extender compound of formula (I), expressed as the number of moles of each chain extender in the mixture calculated as a percentage, is about 1 to about 50% of the composition.

74. (Currently Amended) The composition of claim 69 wherein the molar percentage of the chain extender compound of formula (I), expressed as the number of moles of each chain extender in the mixture calculated as a percentage, is about 35% to about 45% of the composition.

DI 75. (Original) The composition of claim 63 wherein the diisocyanate is aliphatic or aromatic.

76. (Previously Amended) The composition of claim 75 wherein the diisocyanate is 4,4'-diphenylmethane diisocyanate (MDI); methylene bis (cyclohexyl) diisocyanate (H₁₂MDI); p-phenylene diisocyanate (p-PDI); trans-cyclohexane-1,4-diisocyanate (CHDI); 1,6-diisocyanatohexane (DICH); 1,5-diisocyanato naphthalene (NDI); para-tetramethylxylene diisocyanate (p-TMXDI); meta-tetramethylxylene diisocyanate (m-TMXDI); 2,4-toluene diisocyanate (2,4-TDI); isophorone diisocyanate (IPDI); or a mixture thereof.

77. (Original) The composition of claim 63 wherein the hard segment is present in about 15 wt.% to about 50 wt.% of the composition.

78. (Original) The composition of claim 77 wherein the hard segment is present in about 21.8% to about 50 wt.% of the composition.

79. (Original) The composition of claim 77 wherein the hard segment is present in about 21.8% to about 40 wt.% of the composition.

80. (Original) The composition of claim 63 wherein the soft segment is formed from a polysiloxane macrodiol, a polyether macrodiol, a polyether macrodiamine, or a mixture thereof.

81. (Currently Amended) The composition of claim 63 wherein the soft segment includes a macrodiamine compound of formula (I) where n is about 5 to about 100; and where the number average molecular weight of the macrodiamine compound of formula (I) is about 500 to about 10,000.


82. (Previously Amended) The composition of claim 81 wherein the compound of formula (I) is an amine-terminated polydimethylsiloxane (PDMS).

DI 83. (Previously Amended) The composition of claim 82 wherein the amine-terminated polydimethylsiloxane (PDMS) is bis(3-aminopropyl)-polydimethyl siloxane.

84. (Currently Amended) The composition of claim 81 wherein the soft segment is formed from the macrodiamine compound of formula (I), and a macrodiol, ~~and a macrodiamine~~.

85. (Original) The composition of claim 84 wherein the macrodiol is a polysiloxane macrodiol, a polyether macrodiol, a polyester macrodiol, a polycarbonate macrodiol, or a mixture thereof.

86. (Previously Amended) The composition of claim 85 wherein the polysiloxane macrodiol is a compound of formula (II):



wherein

R_9 , R_{10} , R_{11} , R_{12} , R_{13} and R_{14} are each independently an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical; and

p is an integer of 1 to 100.

D 87. (Previously Amended) The composition of claim 86 wherein the compound of formula (II) is polydimethylsiloxane (PDMS).


88. (Original) The composition of claim 87 wherein R_{13} and R_{14} are each independently propylene, butylene, pentylene, hexylene, ethoxypropyl, propoxypropyl, or butoxypropyl.

89. (Previously Amended) The composition of claim 86 wherein the number average molecular weight of the compound of formula (II) is about 200 to about 6,000.

90. (Previously Amended) The composition of claim 86 wherein the number average molecular weight of the compound of formula (II) is about 500 to about 2,000.

91. (Currently Amended) The composition of claim 84 wherein the ~~soft segment is formed from macrodiamine compound of formula (I)~~ is an amine-terminated polydimethylsiloxane (PDMS) and the macrodiol is polydimethylsiloxane (PDMS).

92. (Original) The composition of claim 85 wherein the polyether macrodiol is a compound of formula (III);



wherein

q is an integer of 4 or more; and

r is an integer of 2 to 50.

93. (Previously Amended) The composition of claim 92 wherein q is 5 or higher.

94. (Original) The composition of claim 93 wherein the compound of formula (III) is poly(hexamethylene oxide) (PHMO); poly(heptamethylene oxide); poly(octamethylene oxide) (POMO); or poly(decamethylene oxide) (PDMO).

95. (Previously Amended) The composition of claim 92 wherein the soft segment is formed from the macrodiamine compound of formula (I); and the macrodiol compound of formula (III).


96. (Previously Amended) The composition of claim 92 wherein the number average molecular weight of the compound of formula (III) is about 200 to about 5,000.

97. (Previously Amended) The composition of claim 96 wherein the number average molecular weight of the compound of formula (III) is about 500 to about 1,200.

98. (Currently Amended) The composition of claim 85 wherein the polycarbonate macrodiol is a poly(alkylene carbonate); a polycarbonate prepared by reacting an alkylene carbonate with an alkanediol; a silicon polycarbonate prepared by reacting an alkylene carbonate with 1,3-bis(4-hydroxybutyl)-1,1,3,3-tetramethyldisiloxane (BHTD); ~~an alkanediol~~; or a mixture thereof.

99. (Original) The composition of claim 85 wherein both the polyether macrodiol and the polycarbonate macrodiol are present as a mixture or a copolymer.

100. (Previously Amended) The composition of claim 99 wherein the copolymer is a copoly(ether carbonate) macrodiol represented by the compound of formula (IV):



wherein

R_{15} and R_{16} are each independently an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical; and s and t are integers of 1 to 20.

101. (Currently Amended) The composition of claim 84 wherein the soft segment further comprises macrodiamine is a polyether macrodiamine.

102. (Previously Amended) The composition of claim 101 wherein the polyether macrodiamine is an amine terminated polytetramethyleneoxide.

103. (Currently Amended) The composition of claim 63 wherein the soft segment is formed from the macrodiamine compound of formula (I), a macrodiol, and a polyether macrodiamine.


104. (Currently Amended) A polyurethane-urea elastomeric composition comprising a soft segment and a hard segment, wherein the soft segment is formed from:

a macrodiol comprising a polysiloxane macrodiol and a polyether macrodiol;

and wherein the hard segment is formed from:

a diisocyanate; and

a first chain extender diamine compound of formula (I):



wherein

R is hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₁, R₂, R₃, and R₄ are each independently hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₅ and R₆ are each independently an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₇ is a divalent linking group or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;


n is an integer of 1 to 4; and

the molecular weight of the compound of formula (I) is about 500 or less;

and

a second chain extender selected from the group consisting of:

— a) a compound of formula (I):



wherein

~~— R is hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;~~

~~— R₁, R₂, R₃, R₄, R₅ and R₆ are each independently hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;~~

~~— R₇ is a divalent linking group or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical; and~~

~~— n is an integer of 1 to 4;~~

~~— the molecular weight of the compound of formula (I) is about 500 or less;~~

b) 1,3-bis(3-aminopropyl)tetramethyldisiloxane;

c) 1,3-bis(4-aminobutyl)tetramethyldisiloxane;

d) 1,4-butanediol;

e) 1,2-ethylenediamine;

f) ethanolamine;

hexamethylenediamine;

g) 1,4-butanediamine;

h) water;

i) 1,4-bis(4-hydroxybutyl)tetramethyldisiloxane; and

j) combinations thereof.

105. (Original) The composition of claim 104 wherein the weight ratio of polysiloxane macrodiol to polyether macrodiol in the composition is about 1:99 to about 99:1.

106. (Previously Amended) The composition of claim 104 wherein the weight ratio of polysiloxane macrodiol to polyether macrodiol is about 75:25 to about 85:15.

107. (Previously Amended) The composition of claim 104 wherein the weight percentage of the macrodiol in the composition is about 60 wt.% to about 40 wt.%.

108. (Previously Amended) The composition of claim 104 wherein the diisocyanate is MDI.

109-110 (CANCELED).


111. (Currently Amended) A polyurethane-urea elastomeric composition comprising a soft segment and a hard segment, wherein the soft segment is formed from:

a macrodiol selected from the group consisting of a polysiloxane macrodiol, a polyether macrodiol, a polyester macrodiol, and a polycarbonate macrodiol, or a polyether macrodiamine, and mixtures thereof;

and wherein the hard segment is formed from:

a diisocyanate; and

a chain extender comprising a diamine compound of formula (I):



(I)

wherein

R is hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₁, R₂, R₃, and R₄, ~~R₄, R₅ and R₆~~ are each independently hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₅ and R₆ are each independently an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₇ is a divalent linking group or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical; ~~and~~

n is an integer of 1 to 4; and

wherein the diamine compound of formula (I) has a molecular weight of about 500 or less.


112. (Currently Amended) A polyurethane-urea elastomeric composition comprising a soft segment and a hard segment, wherein the soft segment is formed from:

a macrodiol comprising a polysiloxane macrodiol and a polycarbonate macrodiol;

and the hard segment is formed from:

a diisocyanate; and

a first chain extender diamine compound of formula (I):



wherein

R is hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₁, R₂, R₃, and R₄ are each independently hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₅ and R₆ are each independently an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

R₇ is a divalent linking group or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;


n is an integer of 1 to 4; and

the molecular weight of the diamine compound of formula (I) is about 500 or less;

and

a second chain extender selected from the group consisting of:

—— a) a compound of formula (f):



wherein

— R is hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

— R₁, R₂, R₃, R₄, R₅ and R₆ are each independently hydrogen or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical;

— R₇ is a divalent linking group or an optionally substituted straight chain, branched or cyclic, saturated or unsaturated hydrocarbon radical; and

— n is an integer of 1 to 4; and

— the compound of formula (I) has a molecular weight of about 500 or less;

b) 1,3-bis(3-aminopropyl)tetramethyldisiloxane;

c) 1,3-bis(4-aminobutyl)tetramethyldisiloxane;

d) 1,4-butanediol;

e) 1,2-ethylenediamine;

f) ethanolamine;

g) hexamethylenediamine- hexamethylenediamine;

h) 1,4-butanediamine;

i) water;

j) 1,4-bis(4-hydroxybutyl)tetramethyldisiloxane; and

k) combinations thereof;

wherein the level of hard segment in the composition is about 21.8 wt.% to about 60 wt.%.

113-116 (CANCELED).

117. (Previously Amended) A biomaterial that is manufactured from a composition of claim 63.

118. (Previously Amended) A medical device, article or implant composed wholly or partly of the composition of claim 63.

DI 119. (Currently Amended) The medical device, article or implant of claim 118 which is a cardiac pacemaker, defibrillator, electromedical device, catheters, cannula, implantable prostheses, cardiac assist device, heart valve, vein valve, vascular graft, extra-corporeal device, ~~artificial organ~~, pacemaker lead, defibrillator lead, blood pump, balloon pump, A-V shunt, biosensor, membranes for cell encapsulation, drug delivery device, wound dressing, artificial joint, orthopaedic implant, or soft tissue replacement.

120. (Original) A device or article composed wholly or partly of the composition of claim 63.

121. (Previously Amended) The device or article of claim 120 which is artificial leather, a shoe sole, cable sheathing, varnish, coating, structural components for a pump, structural components for a vehicle, mining ore screen, conveyor belt, laminating compound, textile, separation membrane, sealants or a component of an adhesive.

122-124 (CANCELED).

125. (Currently Amended) The medical device, article or implant of claim 118 having a cyclic-flex fatigue resistance of ~~greater than about~~ 295 million cycles.

126. (Currently Amended) The medical device, article or implant of claim 118 having a degradation resistance ranking of from ~~about~~ 0.7 to ~~about~~ 24.9.

AMENDMENT AND RESPONSE TO OFFICE ACTION

Serial Number: 09/933,938

Filing Date: August 21, 2001

Title: SILOXANE-CONTAINING POLYURETHANE-UREA COMPOSITIONS

Page 16

Dkt: 1207.008US1

127. (Currently Amended) The medical device, article or implant of claim 118 having a degradation resistance ranking of from ~~about~~ 0.7 to ~~about~~ 24.9 after ~~about~~ 3 months *in vivo*.

DI 128. (Currently Amended) The medical device, article or implant of claim 118 having a degradation resistance ranking of from ~~about~~ 0.7 to ~~about~~ 2.4 after ~~about~~ 3 months *in vivo*.

129. (New) The medical device, article or implant of claim 118 having a cyclic-flex fatigue resistance of 343 million cycles.
